

IBC Advanced Alloys - Copper Alloys



Product Data Sheet - C17200 Low Hard

Chemical Composition (Weight Percent)

DELIVERING SOLUTIONS						
Alloy	Beryllium	Cobalt	Nickel	Co + Ni	Co + Ni + Fe	Copper
C17200	1.80 – 2.00	-	0.20 min	0.20 min	0.60 max	Balance

Physical and Chemical Properties

DELIVERING SOLUTIONS					
Density lb/in ³	Elastic Modulus (10 ⁶ psi)	Coefficient of Thermal Expansion (in./in./°F)	Thermal Conductivity (btu/ft.hr.°F)	Melting Temperature °F	Heat Capacity (J/gK)
0.302	19	9.7 x10 ⁻⁶	90	1600-1800	0.44

Typical Mechanical Properties

DELIVERING SOLUTIONS							
Alloy	Temper	Thickness	Tensile Strength ksi	0.2% Offset Yield ksi	Elongation	Hardness HRc or HRb	Electrical Conductivity % IACS
C17200 Plate	AT(TF00)	All sizes	140	110	15	C30	22 min.
C17200 Rounds	AT(TF00)	Over 3" dia	165-200	130-175	15	C30	22 min.

Forms Available:

Plate: Thickness 1.00 to 18.00 inches, width 36 inches max. x standard mill lengths up to 115 inches.

Rounds: Diameter 1.00 to 18.00 inches, standard mill lengths.

Rings: To 55.0 inches O.D.

COPPER ALLOYS

404 Arvin Road,
Franklin, IN 46131
TF: 800.423.5612
T: 317.738.2558
E: coppersales@ibcadvancedalloys.com